



# **BROTHER Strong Adhesive Tape – Technical Data Sheet**

BROTHER INDUSTRIES LTD.

Ver.1.0

20 May 2021

## **Contents**

1. General.....	2
2. Regulatory/Agency Approvals.....	2
3. Colors and Sizes.....	2
4. Physical Properties.....	3
5. Test Results.....	4
5.1 Flat Surface Adhesion – Textured Surface.....	4
5.2 Flat Surface Adhesion – Temperature Ratings (based on the UL969 test results) ..	5
5.3 Tack.....	8
5.4 Chemical/Solvent Resistance (Wiping) .....	9
6. Notes .....	10



## 1. General

Printing Technology:	Thermal Transfer
Label Type:	Strong adhesive
Application:	General identification for textured surfaces

## 2. Regulatory/Agency Approvals

The Strong Adhesive Tape is UL-Recognized to the UL969 Labeling and Marking Standard. For more information, see the UL file MH21016.

The Strong Adhesive Tape complies with the regulations for hazardous chemicals described in the EU RoHS directive. For more information, see “BROTHER GROUP GREEN PROCUREMENT STANDARD” at <http://global.brother>.

## 3. Colors and Sizes

Model Number	Print Color	Tape Color	Width
TZe-S121	Black	Clear	9 mm (0.35 in)
TZe-S131	Black	Clear	12 mm (0.47 in)
TZe-S135	White	Clear	36 mm (1.4 in)
TZe-S141	Black	Clear	18 mm (0.7 in)
TZe-S151	Black	Clear	24 mm (0.94 in)
TZe-S211	Black	White	9 mm (0.35 in)
TZe-S221	Black	White	12 mm (0.47 in)
TZe-S231	Black	White	12 mm (0.47 in)
TZe-S241	Black	White	18 mm (0.7 in)
TZe-S251	Black	White	24 mm (0.94 in)
TZe-S261	Black	White	6 mm (0.23 in)
TZe-S621	Black	Yellow	36 mm (1.4 in)
TZe-S631	Black	Yellow	9 mm (0.35 in)
TZe-S641	Black	Yellow	12 mm (0.47 in)
TZe-S651	Black	Yellow	18 mm (0.7 in)
TZe-S661	Black	Yellow	24 mm (0.94 in)
TZe-SM941	Black	Matte Silver	36 mm (1.4 in)
TZe-SM951	Black	Matte Silver	18 mm (0.7 in)
TZe-SM961	Black	Matte Silver	24 mm (0.94 in)

## 4. Physical Properties

- Thickness (Including the backing paper): approximately 140  $\mu\text{m}$
- Thickness (Excluding the backing paper): approximately 80  $\mu\text{m}$

Adhesive type: Acrylic adhesive

## 5. Test Results

### 5.1 Flat Surface Adhesion – Textured Surface

#### Test Method

In accordance with "10. Adhesive property" in *JIS Z 0237 (2009): Testing methods of pressure-sensitive adhesive tapes and sheets*.

#### Test Conditions

Peeling angle	180°
Temperature and humidity	23°C ±2°C, 50% ±5% RH
Load cell capacity	50 N
Crimping roller mass	2 kg
Test speed	300 mm/min
Adhesive strength calculation range	Average load by the test device in the stroke range from 50 mm to 100 mm
Standing conditions	Room temperature (23°C ±2°C, 50% ±5% RH)
Standing time	<ul style="list-style-type: none"> <li>• 30 minutes</li> <li>• 14 days</li> <li>• 30 days</li> </ul>
Test equipment	Autograph AG-10kNX plus (Shimadzu Corporation)

#### Test Results

Adherend	Average Adhesive Strength [N / 12 mm]		
	After 30 Minutes	After 14 Days	After 30 Days
SUS	6.90	8.31	9.30
PE Textured Board	1.54	2.43	1.29
PP Textured Board	2.79	2.63	2.69
Ac Textured Board	2.97	3.19	3.46
PET Textured Board	3.26	3.98	4.31
PA Textured Board	3.98	4.64	4.62

Test data sources: Allion Japan Inc

## 5.2 Flat Surface Adhesion – Temperature Ratings (based on the UL969 test results)

○ Readable and not peeling off

Model Number	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use
TZe-S121 TZe-S131 TZe-S141 TZe-S151	Acrylonitrile butadiene styrene	100	-30	○	○
	Alkyd paint	100	-30	○	○
	Aluminum	100	-30	○	○
	Galvanized steel	100	-30	○	○
	Phenolic - Phenol Formaldehyde	100	-30	○	○
	Polycarbonate	100	-30	○	○
	Polyester	100	-30	○	○
	Polyester paint	100	-30	○	○
	Polyphenylene oxide/ether	100	-30	○	○
	Polyvinyl chloride	100	-30	○	○
	Stainless steel	100	-30	○	○

Model Number	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use
TZe-S135	Acrylonitrile butadiene styrene	100	-30	○	○
	Alkyd paint	100	-30	○	○
	Aluminum	100	-30	○	○
	Galvanized steel	100	-30	○	○
	Phenolic - Phenol Formaldehyde	100	-30	○	○
	Polycarbonate	100	-30	○	○
	Polyester	100	-30	○	○
	Polyester paint	100	-30	○	○
	Polyphenylene oxide/ether	100	-30	○	○
	Polyvinyl chloride	100	-30	○	○
	Stainless steel	100	-30	○	○

Model Number	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use
TZe-S211	Acrylonitrile butadiene styrene	100	-30	○	○
TZe-S221	Alkyd paint	100	-30	○	○
TZe-S231	Aluminum	100	-30	○	○
TZe-S241	Galvanized steel	100	-30	○	○
TZe-S251	Nylon - Polyamide	100	-30	○	○
TZe-S261	Phenolic - Phenol Formaldehyde	100	-30	○	○
	Polycarbonate	100	-30	○	○
	Polyester	100	-30	○	○
	Polyester paint	100	-30	○	○
	Polyphenylene oxide/ether	100	-30	○	○
	Polyvinyl chloride	100	-30	○	○
	Stainless steel	100	-30	○	○

Model Number	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use
TZe-S621	Acrylonitrile butadiene styrene	100	-30	○	○
TZe-S631	Alkyd paint	100	-30	○	○
TZe-S641	Aluminum	100	-30	○	○
TZe-S651	Galvanized steel	100	-30	○	○
TZe-S661	Nylon - Polyamide	100	-30	○	○
	Phenolic - Phenol Formaldehyde	100	-30	○	○
	Polycarbonate	100	-30	○	○
	Polyester	100	-30	○	○
	Polyester paint	100	-30	○	○
	Polyphenylene oxide/ether	100	-30	○	○
	Polyvinyl chloride	100	-30	○	○
	Stainless steel	100	-30	○	○

Model Number	Application Surface	Max Temp (°C)	Min Temp (°C)	Indoor Use	Outdoor Use
TZe-SM941 TZe-SM951 TZe-SM961	Acrylonitrile butadiene styrene	100	-30	○	○
	Alkyd paint	100	-30	○	○
	Aluminum	100	-30	○	○
	Galvanized steel	100	-30	○	○
	Nylon - Polyamide	100	-30	○	○
	Phenolic - Phenol Formaldehyde	100	-30	○	○
	Polycarbonate	100	-30	○	○
	Polyester	100	-30	○	○
	Polyester paint	100	-30	○	○
	Polyphenylene oxide/ether	100	-30	○	○
	Polypropylene	100	-30	○	○
	Polyvinyl chloride	100	-30	○	○
	Stainless steel	100	-30	○	○

## 5.3 Tack

### Test Method

Probe Tack Test

### Test Conditions

Contact speed	1 cm/s
Hold time	1 s
Peeling speed	1 cm/s
Probe size	$\phi 5.05 \div 0.2[\text{cm}^2]$
Testing equipment	TESTER SANGYO CO., LTD. /TE-6001 Probe Tack Tester

### Test Results

Model Number	Tack Strength
TZe-S121	2.23 N
TZe-S131	
TZe-S135	
TZe-S141	
TZe-S151	
TZe-S211	
TZe-S221	
TZe-S231	
TZe-S241	
TZe-S251	
TZe-S261	
TZe-S621	
TZe-S631	
TZe-S641	
TZe-S651	
TZe-S661	
TZe-SM941	
TZe-SM951	
TZe-SM961	



## 5.4 Chemical/Solvent Resistance (Wiping)

### Test Method

1. Place a 12 mm-wide label on a glass plate.
2. Dampen a piece of cloth with a chemical/solvent, and then wipe the tape with the cloth. Observe the surface for changes.

### Test Conditions

- Label size: 12 mm (width) × 24 mm (length)
- Cassette condition: Two weeks after production, stored at room temperature (23°C ±2°C)
- Environmental conditions during application: Room temperature and humidity (23°C ±2°C, 50% ±10%)
- Application conditions: Pressing down with a roller one way and back at a pressure of approximately 2 kg.

- Readable and not peeling off

Chemical/Solvent	Result
Water	<input type="radio"/>
0.1N HCL	<input type="radio"/>
0.1N NaOH	<input type="radio"/>
Toluene	<input type="radio"/>
Hexane	<input type="radio"/>
Ethyl Alcohol	<input type="radio"/>
Ethyl Acetate	<input type="radio"/>
Acetone	<input type="radio"/>
Mineral Spirits	<input type="radio"/>

## 6. Notes

1. From among the many different types of available tapes, a random sample was selected and used to perform these tests. Accordingly, the results of these tests may differ slightly, depending on the type of tape used.
2. The test results were acquired under specific conditions arranged by Brother. Brother does not guarantee the strength, safety, or accuracy of the numerical data presented in this report.
3. The tape adherence performance can be affected by the material that the tape is attached to, the material's surface condition (whether it is greasy, dusty, rough or curved), the material's shape, and the environmental conditions. Users should confirm the adherence performance under their actual usage conditions after purchasing this product and use the product under their own responsibility.
4. We assume no responsibility for any damage, injuries, or lost profit arising from the use of labels created according to the information contained in this document.